



## TEKNISKE DATA

## Egenskaper

## Norm

## Enhet

## Mineral fx PUR

## Mineral fx PUR

Heterogen PVC.

Leveres i rull.



100% RESIRKULERBAR



### Polyflor Nordic

Kjelsåsveien 168 B

0884 OSLO

Tel.: 23 00 84 00

Fax: 23 00 84 10

[firmapost@polyflor.no](mailto:firmapost@polyflor.no)

[www.polyflor.no](http://www.polyflor.no)

TEKNISKE DATA	Egenskaper	Norm	Enhet	Mineral fx PUR
	Type	EN 649		Heterogen PVC
	Overflate			PUR
	Mønster			Ensfarget
	Farger			14
	Totalvekt	EN 430	g/m <sup>2</sup>	2.700
	Klassifisering	EN 649		23, 34, 43
	Totaltykkelse	EN 428	mm	2,0
	Slitesjikt	EN 429	mm	0,7
	Format rull	EN 426	m	2 m x 20 m / 40 m <sup>2</sup>
	Restinntrykk	EN 433	mm	< 0,1
	Lysekthet	ISO 105-B02 Metode A		≥ 6
	Brann	EN 13501-1		Bfl – S1
	Friksjon	AS/NZS 4586 DIN 51130 EN 13893		R10 R10 DS
	Trinnlyd	ISO 717/2	dB	-
	Elektrisk oppladning	EN 1815	kV	< 2 (antistatisk)
	El. motstand	EN 1081	Ohm	-
	Kjemikaliebestandighet	EN 423		*
	Slitasjegruppe	EN 649		T
	Varmekabler			Ja, ikke over 27°C
	Trinsestolfast	EN 425		Ja, type W, EN 12529
	* Motstandsdyktig. Ved lengre tids påvirkning eventuelt høy konsentrasjon, vennligst ta kontakt.			