

TEKNISKE DATA	Egenskaper	Norm	Enhet	Bisam Effect teppe	
<p><b>Bisam Effect teppe</b></p>    <p><b>POLYFLOR™</b> COVERING THE WORLD</p> <p><b>Polyflor Nordic</b> Kjelsåsveien 168 B 0884 OSLO Tel.: 23 00 84 00 Fax: 23 00 84 10 <a href="mailto:firmapost@polyflor.no">firmapost@polyflor.no</a> <a href="http://www.polyflor.no">www.polyflor.no</a></p>	Produksjonsteknikk			Tufting	
	Overflatestruktur	EN 1307		1/10" velour mønstret	
	Klassifisering	EN 1307		32	
	Mønsterrapport			cm	Ingen rapport
	Garntype				100% Polyamid
	Bakside				texback®contract
	Bredde	Rull		cm	400 cm
	Total tykkelse	EN 1307		mm	7,6
	Total vekt	EN 1307		gr/m <sup>2</sup>	1.770
	Tetthet	EN 1307		per dm <sup>2</sup>	2.054
	Garnvekt	EN 1307		g/m <sup>2</sup>	1.070
	Luvhøyde over bærer	EN 1307		mm	5,6
	Dimensjonsstabilitet				-
	Lysekthet	DIN EN ISO 105-B02			≥ 5
	Brann	DIN EN 13501-1			Cfl-S1
	Varmekabler				ja, ikke over 27°C
	Trinnlyd	DIN EN ISO 717-2			26 dB